



DAMOON CHOOB

PINE
THERMO-D DATA SHEET

DAMOON THERMOWOOD



Thermo-D


- 212 c
- dark brown
- Interior and exterior
- durability and stability



-حرف D مخفف کلمه (durability) یا به زبان فارسی دوام میباشد. ویژگی های کلیدی این محصول در فرآیند تولیدی کلاس D, رنگ قهوه ای تیره, رطوبت 4 الی 5 درصد و انقباض و انبساط حداقلی میباشد. که طبق استاندارد EN113 جز محصولات با دوام قرار میگیرد.

-چوب ترمو نرم کلاس D در دمای 212 درجه به عمل می آید و رطوبت آن 4 الی 5 درصد میباشد.

-چوب ترمو سخت کلاس D در دمای 200 درجه به عمل می آید.



Thermo-S

- 190 c
- gold brown
- interior
- stability

-حرف S مخفف کلمه (stability) یا به زبان فارسی ثبات میباشد. ویژگی های کلیدی و اصلی این محصول در فرآیند تولید کلاس S, رنگ طلایی-قهوه ای روشن, انقباض و انبساط حداقل و رطوبت 6 الی 8 درصد است. که طبق استاندارد EN113 جز محصولات نسبتاً با دوام قرار میگیرد.

-چوب ترمو نرم کلاس S در دمای 190 درجه به عمل می آید و رطوبت آن 6 الی 8 درصد میباشد.

-چوب ترمو سخت کلاس S در دمای 185 درجه به عمل می آید

Mechanical Properties, Strength values	Pine, Kiln-dried	Pine, Thermowood
Modules of elasticity (MOE), flatwise (MPa-N/mm2) DIN EN 408, TS 2478	8529	7411
Modules of rupture (MOR), flatwise (MPa) DIN EN 408, TS 2474	76	31-42
Impact bending strength (IBS), flatwise (MPa) TS 2477	0.43	0.16
Compressive strength (CS), (MPa) TS 2595	42	44

Dimensional Stability 65%Rh 20o C (Increased Stability) (Minimized deformations) (Minimized Expansion and Shrinkage)	Pine, Kiln-dried	Pine, Thermowood
Maximum swelling ratio, tangential (SW-T) (%) DIN 52184, TS 4083, 4084	8.6	3.22
Maximum swelling ratio, radial (SW-R) (%) TS 4083, 4084	4.42	1.5
Maximum swelling ratio, longitudinal (SW-L) (%) TS 4083, 4084	0.18	0.07
Maximum shrinkage ratio, tangential (Sh-T) (%) TS 4083, 4084	7.26	3.62
Maximum shrinkage ratio, radial (Sh-R) (%) TS 4083, 4084	4	1.79
Maximum shrinkage ratio, longitudinal (Sh-L) (%) TS 4083, 4084	0.16	0.08

Physical Properties, Moisture content	Pine, Kiln-dried	Pine, Thermowood
Equilibrium moisture content at 20/65 (%) EN 13183-1	11,6 (9-12)	4(4-6)
Raw density at 20/65 (kg/m3) DIN 52182	434-470	362-404

Biological durability against wood-decaying basidiomycetes (Increased durability to decay) (Resins and sugars removed) (Low moisture content prevents decay and fungi growth)	Pine, Kiln-dried	Pine, Thermowood
Preliminary durability classification Median mass loss (< 5 %) CEN/TS 15083-1	-	class2

Surface burning characteristics of buildings material- Fire resistance.
(Improved fire-resistance)

	Pine, Kiln-dried	Pine, Thermowood
Fire Resistance (UNCOATED) EN 13823	Class Smoke Production Flaming droplets/particles	D S2 d0
Fire Resistance (COATED by using fire retardancy liquids) (immersed/impregnated wood) EN 13823	Class Smoke Production Flaming droplets/particles	A2/B S1 d0

Nail and screw holding strength
(screw withdrawal strength)

	Pine, Kiln-dried	Pine, Thermowood
a. Stainless steel or galvanised screws and plastic clips are recommended. Hidden and face fixing systems EN 1383, NEN 6562 b. Steel material standard 10088-3	-	Class A2
Surface contaminations from fixation elements	-	Not delicate

Glueing

	Pine, Kiln-dried	Pine, Thermowood
Fingerjoints Laminations Panel production	-	MUF, Polyurethane

Brinell Hardness

	Pine, Kiln-dried	Pine, Thermowood
	-	15 N/mm2

Emissions

	Pine, Kiln-dried	Pine, Thermowood
The emissions are not harmful in fresh air.	-	OK
The smell of thermowood products may disappear within a few days but with the surface treatment or rain it may raise up again. 100 % natural, environmentally friendly and recyclable products	-	Short Time

Thermal conductivity, Insulation
(Decreased Thermal Conductivity)

	Pine, Kiln-dried	Pine, Thermowood
Heat conductivity W/mK TS EN 12667	1.2	0.099

Colour

	Pine, Kiln-dried	Pine, Thermowood
Colour of the wood changes (Pine colour is dark brown)	-	OK
Oil and water based coatings	-	OK

Environment (100 % naturel) (recycleable) (from renewable forests)	Pine, Kiln-dried	Pine, Thermowood
PEFC certified	-	OK
100 % naturel	OK	OK
100 % recyclable and biodegradable	OK	OK
Low processing energy demand	OK	OK
Sustainable development and a low carbon future	OK	OK
Wood industries on fast grown plantation wood	OK	OK
From sustainably managed forests	OK	OK

Healty and safety	Pine, Kiln-dried	Pine, Thermowood
Definitely naturel and harmless. Free of chemicals.	OK	OK
Completely healthy.	OK	OK
Improving the stability and durability of wood without using any persistent toxic chemicals	OK	OK

Freeze-heat shock treatments	Pine, Kiln-dried	Pine, Thermowood
1 Cycle: Freezing stage: 3 days -40°C as frozen wood and then Heating stage: 30 min 200°C in furnace as thermal shock effects.	-	OK-5 cycle (surfacequility) (no cracks) (no color change)



DAMOONCHOOB



021-40338910



damoonchoob.co



damoonchoob.com